

## WELDING PROCEDURE SPECIFICATION

WPS - 2007-Intx-8-A REV. NO.: 1 DATE: 4/22/2010 \*\*APPLICABILITY\*\*

WELDING PROCESS: GTAW-A and ASME: X AWS: OTHER: DOE STD-3013-2003

**SUPPORTING PQR:** IC-PQR-02

JOINT: This WPS shall be used in conjunction with the General Welding Standards (GWS) and Welding Fabrication Procedure (WFP) sections and criteria for joint details, repairs, NDE, inspection etc.

Weld Joint Type: Square butt Class: Full penetration See GWS 1-06 and WFP's for joint details Preparation: Machined - Clean with 100% ethyl alcohol < 0.005 **Backing:** None (in glovebox) **Root Opening: Backgrind root:** N/A **Backing Mat.:** GTAW Flux: N/A **Bkgrd Method:** N/A **Backing Retainer:** N/A N/A N/A **FILLER METALS:** Class: and

Insert: N/A Insert Desc.: N/A Weld Metal Thickness Ranges:

Flux: Type: N/A Size: N/A AWS Root Pass: 0 thru 0 Filler Metal Note: N/A Autogenous weld AWS Balance: 0 thru 0

ASME Root Pass: 0.05 thru 0.1
ASME Balance: 0.05 thru 0.1

BASE MATERIAL P/S No. 8 Gr No. All to: P/S No. 8 Gr No. All Spec. A-276 SS- Bar Grade: All to: Spec. A-276 SS- Bar Grade: All

Qualified Pipe Dia. Range:  $\geq$  AWS: 0 ASME:

Qualified Thickness Range: AWS: 0.000 thru 0.000 ASME: 0.050 thru 0.100

V/Up-Dn **OUALIFIED POSITIONS:** AWS: N/A ASME: All Vert. Prog.: Preheat Min. Temp.: 70°F **GAS: Shielding:** He or Gas Composition: 100 / 350°F % **Interpass Max. Temp.:** % N/A°F Gas Flow Rate cfh: 10 20 **Preheat Maintenance:** to to PWHT: Time @ °F Temp. N/A **Backing Gas/Comp:** He\* 100 % Temp. Range: N/A°F **Backing Gas Flow cfh:** 0 0 to N/A °F Trailing Gas/Comp: He\* 100 % to

**APPROVAL:** Signatures on file at ENG **DATE:** 4/22/2010

Monday, June 07, 2010 Page 1 of 2

WPS NO: 2007-Intx-8-A

WELDING CHARACTERISTICS:

Current: DCEN and DCEN Tungsten Type: EWTH-2 Transfer Mode: N/A

Ranges: Amps 7 to 80 Tungsten Dia.: 0.035 Pulsing Cycle: 60 to 40

Volts to Background Current: 7

Fuel Gas: N/A Flame: N/A Braze temp. °F N/A to N/A

WELDING TECHNIQUE: For fabrication specific requirements such as fittup, cleaning, grinding, PWHT and

inspection criteria refer to Volume 2, Welding Fabrication Procedures

Technique: Automatic part rotated Cleaning Method: Abrasive cloth/Ethel alcohol

Single Pass or Multi Pass: S Stringer or Weave bead (S/W): S or Oscillation: N/A

GMAW Gun Angle °: 0 to 0 Forehand or Backhand for GMAW (F/B): N/A

No Pass >1/2": GMAW/FCAW Tube to work distance: N/A

Maximum K/J Heat Input: N/A Travel speed: 6 ipm Gas Cup Size: 0.150

PROCEDURE QUALIFIED FOR:

Charpy "V" Notch: N/A Nil-Ductil Transition Temperature: N/A Dynamic Tear: N/A

Comments: 1) Voltage is fixed with arc gap length of 0.055 - 0.075 in rotating welding head.

2) All welding is performed in a Helium atmosphere inside a glove-box.

Weld Layer	Manual Process	Filler Metals	Size	Amp Range		ange	Volt Range	Travel/ipm	Nozzle Angle	Other
1	GTAW-A	N/A	N/A	7	to	80	to	0 <b>to</b> 6	0 <b>to</b> 0	
2		N/A	N/A	0	to	0	to	to		
3		N/A	N/A	0	to	0	to	to		
4		N/A	N/A	0	to	0	to	to		

REM. \* Weld layers are representative only - actual number of passes and layer sequence may vary.

ML-1/2 projects or jobs must determine if the supporting documentation for this WPS complies with quality requirements of the project/job.

Use of LANL Welding Procedures and Welder Qualifications for non-LANL work shall be at the sole risk and responsibility of the Subcontractor, and the Subcontractor shall indemnify and save LANL and the Government harmless from any and all claims, demands, actions or causes of action, and for any expense or loss by reason of Subcontractor's and their employees posession and use of LANL procedures and qualifications.

Monday, June 07, 2010 Page 2 of 2