



WELDING PROCEDURE SPECIFICATION

WPS - 3001-11B **REV. NO.:** 0 **DATE:** 10/6/2004 ****APPLICABILITY****
WELDING PROCESS/ES: GMAW and GMAW **ASME:** X **AWS:** X
SUPPORTING PQR: Z-WS-8-G-V Z-WS-8-H **OTHER:** AISC

JOINT This WPS shall be used in conjunction with the General Welding Standards (GWS) and Welding Fabrication Procedure (WFP) sections and criteria for joint details, repairs, NDE, inspection etc.

Weld Joint Type: Groove/fillet	Class: Full/partial penetration
See GWS 1-06 for joint details	Preparation: Mechanical/thermal
Root Opening: 1/16" - 3/16"	Backing: None
Backgrind root: Root/second side	Backing Mat.: CS Strap/ring when used
Bkgrd Method: Grind/chip/arc gouge	GTAW Flux: N/A Backing Retainer: N/A

FILLER METALS:	Class: ER-1xxS-x and -----
A No: 12 SFA Class: 5.28 and --- F No: 6 and --- Size: .045 --- --- ---	Weld Metal Thickness Range:
Insert: N/A Insert Desc.: N/A	AWS: 0.187 thru 8.000
Flux: Type: N/A Size: N/A	ASME: 0.187 thru 8.000

BASE MATERIALS:	P No. 11B Gr No. All to: P No. 11B Gr No. All
Spec. SA-517 Grade: **	to: Spec. SA-517 Grade: **
Qualified Pipe Dia Range: = : 0	
Qualified Thickness Range: AWS: 0.187 thru 8.000	ASME: 0.187 thru 8.000

QUALIFIED POSITIONS: All-plate ----- **Vertical Progression:** V-UP

Preheat Min. Temp.: *70 °F	GAS: Shielding: CO2 or -----
Interpass Max. Temp.: 500 °F	Gas Composition: 100 % 0 % 0 %
Preheat Maintenance: *70 °F	Gas Flow Rate cfh: 25 to 40
	Backing Gas/Comp: None 0 %
PWHT: Time @ °F Temp. N/A	Backing Gas Flow cfh: 0 to 0
Temp. Range: 0 °F to 0 °F	Trailing Gas/Comp: None %

PREPARED BY: KG Fellers **DATE:** 10/6/2004
Signature on file at FWO-DECS

APPROVED BY: Tobin oruch **DATE:** 10/6/2004
Signature on file at FWO-DECS

Note:For SC/SS/ML-1/ML-2 work, this WPS requires independent review.

WELDING CHARACTERISTICS:

Current: DCEP and --- Tungsten type: N/A Transfer Mode: Spray
 Ranges: Amps 180 to 0 Pulsing Cycle: N/A to N/A
 Volts 20 to 0 Background Current: N/A
 Fuel Gas: N/A Flame: N/A Braze temp. °F N/A to N/A

WELDING TECHNIQUE: For cleaning, grinding, and inspection criteria refer to Volume 2, Welding Fabrication Procedures

Technique: Semi-auto Cleaning Method: Grind/chip/arc gouge
 Single Pass or Multi Pass: M Stringer or Weave bead (S/W): S/W Oscillation: N/A
 GMAW Gun Angle °: 5 to 15 Forehand or Backhand for GMAW (F/B): FH
 GMAW/FCAW Tube to work distance: 3/8" - 1/2"
 Maximum K/J Heat Input: N/A Travel speed: As required Gas Cup Size: 1/2"-3/4"

No single pass shall deposit greater than 1/2" thickness of material.

PROCEDURE QUALIFIED FOR:

Charpy "V" Notch: N/A Nil-Ductil Transition Temperature: N/A Dynamic Tear: N/A

Comments: (1) *IPT and Preheat for material =3/4" = 225 °F min. (2) **Grade #s A,B,E,F,J&P

Weld Layer	Manual Process	Filler Metals	Size	Amp Range	Volt Range	Travel/ipm	Nozzel Angle	Other
1	GMAW	ER-1xxS-x	.045	180 to 220	20 to 24	4 to 5	5 - 15	
2	GMAW	-----	---	0 to 0	0 to 0	---- to ----		
3	GMAW	-----	---	0 to 0	0 to 0	---- to ----		
4			---					
5			---					
6								
7								
8								

REM. * Weld layers are representative only - actual number of passes and layer sequence may vary due to variations in joint design, thickness and fitup.

Use of LANL Welding Procedures and Welder Qualifications for non-LANL work shall be at the sole risk and responsibility of the Subcontractor, and the Subcontractor shall indemnify and save LANL and the Government harmless from any and all claims, demands, actions or causes of action, and for any expense or loss by reason of Subcontractor's and their employees possession and use of LANL procedures and qualifications.