

TABLE OF CONTENTS

GWS 1-03	WELDING AND BRAZING MATERIAL PROCUREMENT & CONTROL	3
1.0	Purpose and Scope	3
2.0	References.....	3
3.0	Acronyms and Definitions	3
4.0	General.....	4
5.0	Procedure	4
6.0	Attachments	12
	Attachment 1: Electrode/Storage/Conditioning and Exposure Limits.....	12
	Attachment 2: Weld Material Requisition	12
	Attachment 3: Weld Material Issue Card/ Weld Material Return Card (backside of Issue Card).....	12
	Attachment 4: Weld Wire Usage Log.....	12
	Attachment 5: Filler Metal Procurement Required Tests	12
	Attachment 6: Requirements for Welding Gases.....	12
	Attachment 7: Welding Checklist.....	12

RECORD OF REVISIONS

Rev	Date	Description	POC	OIC
0	8/16/04	Initial issue.	Kelly Bingham, <i>FWO-DECS</i>	Gurinder Grewal, <i>FWO-DO</i>
1	5/18/05	Minor changes to 5.1.A.1, 5.2.C, 5.5.B-C; added Att 7 Welding Checklist.	Kelly Bingham, <i>ENG-DECS</i>	Gurinder Grewal, <i>ENG-CE</i>
2	5/17/06	Added issue station assessment; deleted redundant responsibilities; added 5.5.A.4 & 5 for clarification; clarified 5.5.A.6.	Kelly Bingham, <i>ENG-DECS</i>	Mitch Harris, <i>ENG-DO</i>
3	10/27/06	Organization updates from LANS transition. Controlling document number changes.	Kelly Bingham, <i>FM&E-DES</i>	Kirk Christensen, <i>CENG</i>
4	6/06/08	Corrected audit deficiencies and clarifications throughout.	Kelly Bingham, <i>ES-DE</i>	Kirk Christensen, <i>CENG</i>
5	7/21/08	Clarified filler material return/disposal requirements of Para. 5.6 and 5.8.	Kelly Bingham, <i>ES-DE</i>	Kirk Christensen, <i>CENG</i>
6	7/16/15	Excluded oxygen & acetylene from gas requirements. Clarified when LANL supplies stock filler material. Removed reference to SSS.	David Bingham, <i>ES-DE</i>	Larry Goen, <i>ES-DO</i>
7	5/5/16	Clarified longstanding practice of stocking ML-1 material and allowed ML-3/4 under specific conditions (5.1.A.1-3), improved definitions.	David Bingham, <i>ES-DE</i>	Larry Goen, <i>ES-DO</i>

Contact the Welding Standards POC for upkeep, interpretation, and variance issues

GWS 1-03	<u>Welding POC / Committee</u>
-----------------	--

GWS 1-03 WELDING AND BRAZING MATERIAL PROCUREMENT & CONTROL

1.0 PURPOSE AND SCOPE

1.1 Purpose

- A. To establish and to define consumable welding material procurement and control requirements for the LANL Welding Program in compliance with engineering drawings and specifications, applicable codes and standards, and contract requirements.

1.2 Scope

- A. The scope of this procedure is the procurement and control of weld filler material and welding and purge gases to be used for all welding activities performed by LANL personnel, and to Subcontractors at LANL as invoked by Subcontract documents, in accordance with Reference 1.

2.0 REFERENCES

GWS 1-01, *Introduction & Scope*

GWS 1-05, *Welder Performance Qualification / Certification*

GWS 1-07, *Material Specifications*

GWS 1-09, *Control of Subcontracted Welding*

[Exhibit H/Form 838c](#), *Procurement Quality Requirements*

3.0 ACRONYMS AND DEFINITIONS

Acronym / Term	Description
Certificate of Compliance (C of C)	A signed and dated document that attests to the specifications, characteristics, or attributes of an item or service, or the source material or feedstock for the item, and is provided as an affirmation that the described requirements as specified in the contract or purchase order have been satisfied. If the filler material manufacture has the capability to label the filler material containers with a Certificate of Compliance, in accordance with ASME SFA or AWS requirements, a separate document is not required.
Certified Material Test Report (CMTR) or Certificate of Analysis (C of A)	A certificate issued by the original fabricator of the material, part, or equipment which is traceable to the shipment through a unique identification number and which indicates measured chemical and physical properties as specified in the procurement contract and that the test(s) were performed to applicable nationally recognized standards.

Acronym / Term	Description
SFA	ASME Standard series of AWS A5.XX series filler material specifications that have been officially adopted by ASME B&PV Code.
Welding Consumables	Materials required to weld or braze and do not constitute a desired component of the weldment. These materials include, but are not limited to: tungsten or other non-consumable electrodes, contact tips, ceramic backing, torch parts, weld test coupons, etc.
Welding/Brazing Filler Metal	Materials required by a Welding Procedure Specification (WPS), Brazing Procedure Specification, Welding Fabrication Procedure (WFP), or Welding Technique Sheet (WTS) to produce a welded or brazed joint. These materials include, but are not limited to: coated electrodes, bare filler rods and wire, flux-cored spooled wire, metal core electrodes, fluxes, gasses, pre-placed consumable inserts, weld studs etc.

4.0 GENERAL

4.1 Responsibilities

- A. **LANL Quality Performance Assurance Institutional Quality (QPA-IQ)** is responsible for conducting assessments to authorize weld issue stations and verification activities relating to procurement, receiving, issue, and control of consumable welding filler materials.

5.0 PROCEDURE

- A. Except for special-chemistry¹ materials, all welding and brazing electrodes and wire, including granular fluxes for Submerged Arc Welding (SAW), shall be purchased in accordance with the latest requirements of ASME B&PVC Section II, Part C and/or AWS A5.01 Filler Metal Procurement Guidelines and or AWS 5.1 through 5.36 Filler Material Specifications.
- B. Welding filler material used for ASME Section I BEP (Boilers and Boiler external piping), ASME Section III, ASME Section VIII, ASME B31.3 Category K and M, Safety Class, Safety Significant, nuclear defense in depth, ML-1, and ML-2, welding procedure qualification tests, or Project/Program when specified, shall maintain traceability through the point of use and then filed in the project/program/facility files.

5.1 Procurement of Welding Consumables by or for LANL

Guidance: The LANL Warehouse stocks bulk quantities of common certified filler material for use by LANL and its Subcontractors for whom filler material is to be government furnished by contract.

Other Subcontractors are responsible to supply filler material meeting the requirements defined in GWS 1-03 and attachments.

On a case-by-case basis as authorized by the responsible Subcontractor’s STR, LANL-stocked filler material may be issued and the cost of those materials charged to the LANL project. The STR should require compensation from the subcontractor for the cost of filler material. LANL will disburse daily quantities to those with proper paperwork (see 5.5 below); they will also issue

¹ Special-chemistry filler material is that which does not have an AWS Classification.

bulk quantities to those maintaining WPA-approved satellite and issue stations. A list of stocked filler material is [here](#) under Quick Links.

- A. Procurement of Filler Materials shall comply with the following:
1. Welding Filler Materials (defined in Section 3.0 above) and purchased for use on-site at LANL shall be procured as ML-1 except as noted in Para 3 below.²
 2. Certifications:
 - a. Procurement documents ([Exhibit H](#) or Form [838c](#)) shall require the manufacturer or vendor to supply a Certified Material Test Report (CMTR) for the materials.
 - b. Require actual CMTRs following the guidance of AWS 5.01, *Filler Metal Procurement Guidelines*, Table 2, Schedule I - Required Tests (by AWS Specification). The CMTR shall include the actual results of all chemical analyses, mechanical tests, and examinations as required by Schedule I, and shall be traceable by Lot, Batch, or Heat Number to the material delivered for use (see Attachment 5 for a matrix of required tests).
 - c. A Certificate of Compliance (C of C) may be substituted for a CMTR if approved by the LANL WPA. The C of C shall state that the welding consumables were manufactured in accordance with the requirements of the appropriate material specification for each material type, size, heat, and lot number. The manufacturer or vendor may fulfill this requirement by labeling each container with a statement that the material conforms to the appropriate ASME SFA, AWS, or Engineering specification. If the containers are not labeled, the supplier or manufacturer shall provide a written C of C on supplier or manufacturer letterhead.
 3. On a case-by-case basis, the WPA or LANL Engineering Standards Manager may approve procurement of Welding Filler Material not meeting Paras. 5.1.A.1 and 2 above. Such material shall be marked as ML-3 or ML-4 as appropriate, segregated from warehouse-stocked filler material, stored at the Weld Test Facility, and issued for use by LANL authorized Weld Test Supervisors.³
 4. Low Hydrogen SMAW Electrodes (EXXX5, EXXX6, and EXXX8) shall meet diffusible hydrogen of 4 mL/100grams of deposited weld metal maximum and shall be labeled with the designator H4 as outlined in AWS 5.1 or 5.5 Specifications.
 5. Low Hydrogen FCAW Electrodes (EXXT-X) shall meet diffusible hydrogen of 8 mL/100grams of deposited weld metal maximum and shall be labeled with the designator H8.
- B. Special-chemistry weld filler materials not included in ASME SFA or AWS specifications shall be purchased only after LANL Welding Program Administrator or LANL Engineering Standards Manager approval and shall be procured with CMTRs along with any additional requirements specified in the purchase order.

² Procurement to highest standards eliminates need for segregation and control of higher and lower pedigree materials and the potential for substandard material being used in a nuclear application. Bulk purchase minimizes cost of this approach to institution.

³ Provides tight control with no training impact to most Attendants.

- C. A list of weld filler material types and corresponding AWS classification or ASME SFA specification numbers is provided in GWS 1-07, *Material Specifications*.
- D. Procurement of gases used for welding or purging, except oxygen and acetylene⁴, shall comply with the following:
 - 1. Gases shall be procured with C of A's to meet the purity and dew point requirements of the applicable gas(es) listed in AWS A5.32, *Specification for Welding Gases*; Table 1. The C of A's shall include the actual results of all purity analyses, dew point, and shall be traceable by bottle, Dewar, or bulk system manifold to the material delivered (see Attachment 6 for AWS 5.32, *Specification for Welding Gases*; Table 1 Gas Type, Purity, and Dew Point Requirements.)
 - 2. Gas containers shall either be evacuated or, if not evacuated, residual gases shall be analyzed for composition and purity prior to filling.
 - 3. Each gas of multi-component gas mixture shall be tested for and meet the purity requirements of each specific gas as listed in Table 1.
 - 4. The multi-component gas mixture shall meet the dew point requirement not greater than the highest dew point of the individual gases in the mixture.
 - 5. Procurement documents (Exhibit H or [Form 838c](#)) shall require the manufacturer or supplier to provide a Certificate of Analysis Report (C of A) for gases in accordance with Attachment 6.
 - 6. Welding gases used for ASME Section I BEP (Boilers and Boiler external piping), ASME Section III, ASME Section VIII, and ASME B31.3 Category K and M, Safety Class, Safety Significant, VSS Defense-in-Depth, welding procedure qualification tests, or Project/Program when specified shall maintain traceability through the point of use and then filed in the project/program/facility files.
 - 7. A Certificate of Compliance (C of C) may be substituted for a C of A if approved by the LANL WPA. The C of C shall state that the gases are in accordance with the requirements of the appropriate material specification for each gas. The supplier shall provide a written C of C on supplier or manufacturer letterhead.

5.2 Program Implementation

- A. All weld filler material shall be inspected for shipping damage by LANL QPA-IQ Receipt Inspection or in accordance with approved Subcontractor Quality Program requirements when they procure filler materials for use on LANL property. Copies of procurement documents and receipt inspections by Subcontractors shall be provided to the WPA for review. Any damaged material shall be identified and properly dispositioned prior to release for use.
- B. Certified Material Test Reports or Certificates of Analysis shall be checked against the original purchase order requirements and verified against the chemical and mechanical requirements of the ASME SFA or AWS specification. Discrepancies shall be identified

⁴ Acetylene is not listed in AWS A5.32 and all LANL oxygen sources meet or exceed these specifications

and brought to the attention of the LANL WPA for disposition prior to the release of any material.

- C. Weld filler material shall be stored in a clean, dry, enclosed, and controlled area. The area shall have uniform heating and temperature control to prevent condensation or corrosion. Minimum temperature shall be 40 °F (5 °C) with a maximum temperature of 140 °F. Welding materials shall not be in direct contact with concrete floors and shall be stored on pallets or bins segregated by weld filler material type and size. Multiple stacking of pallet or boxes should be avoided to prevent damage to storage containers.
- D. Bags of granular flux or spooled wire shall be laid flat on pallets or boards, and maintained in their weather-proof storage packets or bags.
- E. Electrodes, wires, etc., shall be stacked separately and segregated from each other, i.e., stainless steel electrodes shall not be stored with carbon steel electrodes and E6010 electrodes shall not be stored with E7018 electrodes.
- F. Wherever possible, different heat numbers or control numbers of a single type of welding material (e.g., E7018) shall be grouped within the stack or kept on separate shelves.

5.3 Local or Field Satellite Storage Areas

- A. Local storage, including field satellite areas, shall be clean, dry and weather tight. Sufficient space and electrical power shall be provided to support electrode storage ovens as well as portable rod ovens or heaters. Access shall be controlled at all times. Issue station or tool room conditions shall be maintained in accordance with § 5.2.C, D, and E.

5.4 Storage Oven Requirements

- A. Coated electrodes of the low-hydrogen type, including series EXXX5, EXXX6 and EXXX8 (such as E7018, E8018-B2L, etc.), shall be stored in welding electrode storage ovens once the hermetically sealed container has been opened. Storage ovens shall be maintained in accordance with Attachment 1 and the following:
 - 1. Each storage oven shall have a tag or label placed on the door identifying the electrodes stored in each section of the oven.
 - 2. The exposure limits described in Attachment 1 shall be followed for all welding material types.

5.5 Weld Filler Material Issue and Control

- A. **Authorized Issue Stations:** Issue stations must be assessed by QPA and authorized by the WPA. Approved stations are listed on the Welding Chapter webpage ([direct link](#)). LANL managers shall determine whether the project size, manpower, scope, and duration warrant a weld filler material issue station staffed by an attendant. If a weld filler material issue station is not implemented at the project, the LANL manager shall ensure that weld filler materials are issued in a manner that will assure appropriate control. Weld filler materials shall not be stored in craft gang boxes, lockers, vehicles, or left in work areas overnight or for the next shift. Unused weld filler materials shall be returned to a storage oven or storage area at the completion of the work assignment or end of shift, whichever occurs first (see 5.8).

1. **Authorized Rod Issue Attendants:** The LANL Manager or Facility Manager or Subcontract STR shall ensure that the Issue Station Attendants:
 - Have a backup (each authorized issue station has two authorized issue attendants)
 - Each Attendant completes Training Plan 9781 - Filler Material Control-Rod Issue Attendant and is authorized by the LANL WPA
 - Issues only the filler metal type and size listed on the Weld Material Requisition.
 - Accurately and legibly records issue transactions on the Weld Material Issue Card and Weld Material Return Card.
 - Maintains weld material identification tags or labels on or in weld material storage ovens or bins.
 - Stores weld material by type and size in ovens or bins whereby the material stored corresponds to the material identification tag or label.
 - Checks the storage oven temperature daily to assure that the oven is functioning and operating at the proper temperature with a calibrated thermometer or other calibrated measuring temperature device (documentation of this check is not necessary).
 - Uniquely numbers or otherwise identifies ovens and or storage bins
 - Maintains the CMTRs or C of Cs for the filler material. Copies can be made and placed in the project package if needed.
 - Maintains the CMTRs or C of Cs for the filler material. Copies can be made and placed in the project package if needed.
2. **Welding Material Requisition:** LANL Managers or Facility Managers or Subcontract STR shall use the Weld Material Requisition (Attachment 2) -- a three part form with white original, pink and yellow copies -- to authorize the specific AWS Designation, size, and quantity of filler material the issue station attendants can issue to welders. In addition, a Welding Checklist (Attachment 7) shall accompany the weld material requisition or must be on file with the tool room attendant in order to verify that the welders are certified and the process and filler material is correct.
3. **Welder Continuity/Renewal:** After filler material is issued to the welder, completed Weld Material Requisitions (white copy shall be sent to the Welding Program WPA for welder continuity updates).
 - For welding applications where there is no filler material used, a Weld Material Requisition may be completed and sent to the WPA with the *material requested* field marked as N/A.
 - Alternatively, continuity/renewal can be accomplished by the Welder's supervision or LANL-approved AWS-CWI sending an e-mail to the WPA providing the welder's Name, Z-No, Welding Process, and the date welding was performed .
4. **Welding Checklist:** The Welding Checklist establishes that requirements for welding have been identified prior to the start of welding and shall include the following information:

- applicable codes and standards or design requirements (such as project specifications and or drawings) if there are no codes,
- welding procedures specifications that will be used for welding,
- names and Z # of certified welders who will be welding,
- correct filler(s) materials to be used,
- required hold points and inspections to meet applicable codes or design

B. **Certified Welding Inspector (AWS-CWI) or WPA-qualified SME** shall verify that the Welding Checklist is correct and complete and sign off as the SME on the Checklist. The tool room attendant or designated person shall verify the Checklist against the material requisition form for filler material and welder names and then issue material if appropriate. Control of the filler material is required to be in place with excluded and exempted welding. The original welding-related documents shall be kept in the job or project document package until project completion. A copy of the Checklist and Weld Material Issue Cards shall be kept with the tool room attendant. After project completion the records shall be forwarded to the facility or project/program record files for retention.

Guidance Note: A test will generally be administered to determine SME qualification

NOTE:
 Filler material used for Excluded and Exempted activities must be physically secured and controlled to prevent cross-contamination with other welding tasks.
 Filler material must only be issued to personnel authorized by their supervisor.
 It is recommended that filler materials used for Excluded and Exempted activities be procured, controlled and issued using the process outlined in Para. 5.5.

- C. **Weld Material Issue:** The issue station attendant shall complete the information listed on the Weld Material Issue Card (Attachment 3), including the useful lifetime (without further preservation for low hydrogen electrodes) of the material being issued.
- D. Weld filler materials that exhibit any of the following conditions shall not be issued:
1. visible damage,
 2. covered electrodes which are oil or water soaked, dirty, or on which the flux has cracked or separated from the core wire,
 3. bare and flux-cored wire that contains rust, is pitted, or has been oil or water soaked, or
 4. electrodes from a hermetically sealed container whose seal has been broken during shipping or handling.
- E. Welders shall not be issued more than one ASME SFA or AWS classification of electrode or weld filler material at any one time. However, when the Welding Fabrication Procedure or Welding Technique Sheet requires more than one welding process or weld filler material type, weld filler metal and electrodes for both processes may be issued at the same time, provided the welder is qualified for both processes. Quantities of weld filler material shall be based on the amount estimated for use on a daily shift basis.

- F. Initial issuance of electrodes may either be directly from the sealed containers or storage ovens into portable rod ovens or heaters. Electrodes issued from storage ovens shall be on approximately a first-in, first-out basis.
- G. At the time of issue, the welder shall be instructed to examine the weld filler material to assure compliance with the material listed on the Weld Material Issue card.
- H. Quantities and types of weld filler materials for use in the Welder Qualification Test facility shall be obtained or procured by the responsible Weld Test Supervisor. Quantities may be obtained or procured as required and stored in the Weld Test Facility. The responsible Weld Test Supervisor shall control exposure times and storage ovens for coated electrodes. Weld Material Requisitions/Issue and Return Cards are not required for welders in the test facility. Only the Weld Test Supervisor shall issue weld filler materials to the welder. See [GWS 1-05](#), *Welder Performance Qualification/Certification*.
- I. In the event of a power outage to the storage ovens, the electrodes, except for the situations described below, shall be discarded or referred to the LANL WPA for resolution.
 - 1. E7018 and E8018 Series Electrodes – If the power outage is 4 hours or less, or if it can be established that the oven temperature did not fall below 120 °F, return the oven to the specified temperature. The electrodes may be issued in the usual manner.
 - 2. E9018, E10018, and E11018 Series Electrodes – If the power outage is 2 hours or less, or if it can be established that the oven temperature did not fall below 160 °F, return the oven to the specified temperature. The electrodes may be issued in the usual manner.
 - 3. Electrodes Other Than Low-Hydrogen Electrodes – If the power outage is 24 hours or less, return the oven to the specified temperature. The electrodes may be issued in the usual manner.
- J. Portable rod ovens or heaters shall be used by the welder at the work area when EXX18 and EXXX18 series (low-hydrogen) electrodes will be exposed to the ambient environment for periods exceeding the maximum exposure time listed in Section 5.7 and the following:
 - 1. Portable rod ovens for EXX18 and EXXX18 series electrodes shall have the thermostats set between 250 °F and 350 °F.
 - 2. Prior to use, the portable rod oven shall be clean and dry. Portable rod ovens in service at welding locations shall be connected to a power supply and energized. Welders shall be instructed or trained to determine whether the portable oven is energized. A red indicator light or temperature indicator on the portable oven may be used to determine whether it is energized. If a welder notices that the oven has cooled below “warm to the hand” temperature or the portable oven is not working, the portable rod oven and all remaining weld filler material shall be returned to the issue station. See preceding paragraph for temperature requirements.

5.6 Control of Welding Filler Material during Welding

Responsible LANL supervisors or craft foremen shall instruct welders in the following production controls and ensure that they are met:

- A. Each welder must complete Training Plan [9780](#) - Filler Material Control-Welder.
- B. Upon reaching the work location, the welder may transfer low-hydrogen electrodes from the portable oven to a leather pouch or other clean and dry holder. Portable rod ovens shall be closed at all times, except when removing electrodes. Electrodes shall not be put back into the portable oven after they have been removed.
- C. The welder shall not weld with low-hydrogen electrodes that have exceeded the exposure times indicated in Section 5.7. This may require posting low-hydrogen electrode exposure times.
- D. Waste ends, stubs, and low-hydrogen electrodes exceeding the exposure requirements of Section 5.7 shall be properly discarded by the welder in a scrap or trash bin.
- E. The welder shall return unused weld filler material when required by Subsection 5.8.
- F. Welding materials shall not be left lying around where inadvertent or intentional use is possible. Spooled wire left on wire feed units shall be protected from damage and contamination.
- G. At all times through point of consumption, bare wire in straight lengths shall retain the manufacturer's flag tag or identification; spooled wire shall retain the spool identification.

5.7 Low-Hydrogen Electrode Exposure Time Limits

- A. Low-hydrogen electrodes shall not be exposed to the ambient environment for a time exceeding the exposure limits in Attachment 1.
- B. Alternative Atmospheric Exposure Periods Established by Test: The alternative exposure time values shown in AWS D1.1 Table 5.1 Column B may be used provided testing establishes the maximum allowable time. The testing shall be performed in conformance with AWS A5.5, Subsection 3.10 for each electrode classification and each electrode manufacturer, and meet all the requirements in AWS A5.5 and be less than the maximum values listed Table 9. In addition, E70XX and E70XX-X (AWS A5.1 & A5.5) shall be limited to maximum moisture content not exceeding 0.04% by weight.

NOTE: When low-hydrogen electrodes are being transferred from their shipping container to the heated storage oven or portable rod oven and vice-versa, the electrodes shall not be considered as having been exposed to the ambient environment.

5.8 Return and Reissue Requirements for Welding Filler Materials

- A. Unused weld filler material, except as noted in Sections 5.8.B, 5.8.C, and 5.8.D, shall be returned by the welder with the Weld Material Return Card (Attachment 3; Note: Weld Material Return Card is on the back side of the Weld Material Issue Card) to the issue station at the end of the shift.
 - 1. The issue station or tool room attendant shall complete the information listed on the Weld Material Return Card and sign on the "Received by" line.
- B. Where the cost to return material to issue station and restock is more than the replacement cost of the material, small amounts of unused filler material may be bent to unusable and properly discarded by the welder in a scrap or trash bin. Also, low-

hydrogen electrodes that have been exposed to the ambient environment shall be discarded.⁵

- C. Low-hydrogen electrodes returned to the issue station in a portable rod oven (have not been exposed to the ambient environment) shall be logged in and placed in a storage oven. These electrodes shall not be issued for a minimum of 8 hours. *This may require maintaining separate storage ovens for each shift to provide proper control.*
- D. Coiled, bare, or flux-cored wire mounted on semiautomatic or automatic welding machines need not be returned at the close of the shift, provided that the wire is covered and protected (kept clean and dry) and will be used within 48 hours.
 - 1. Alternatively, a Weld Wire Usage Log (Attachment 4) maybe filled out for each machine on which wire is stored for use. Other covered electrodes that are returned shall be placed in their storage area or oven until they are reissued.
- E. Bare wire, flux-cored wire, and other weld filler materials shall be placed in their storage location until they are reissued.

6.0 ATTACHMENTS

ATTACHMENT 1: ELECTRODE/STORAGE/CONDITIONING AND EXPOSURE LIMITS

ATTACHMENT 2: WELD MATERIAL REQUISITION

ATTACHMENT 3: WELD MATERIAL ISSUE CARD/ WELD MATERIAL RETURN CARD (BACKSIDE OF ISSUE CARD)

ATTACHMENT 4: WELD WIRE USAGE LOG

ATTACHMENT 5: FILLER METAL PROCUREMENT REQUIRED TESTS

ATTACHMENT 6: REQUIREMENTS FOR WELDING GASES

ATTACHMENT 7: WELDING CHECKLIST

⁵ Cost to return, segregate, and bakeout makes field disposal more cost effective.