



WELDING PROCEDURE SPECIFICATION

WPS: 2015-xxxx-8-A
WELDING PROCESS: GTAW
SUPPORTING PQR:

REV. NO.: 0
CODE: ASME IX

DATE: 12/11/2015
OTHER: **APPLICABILITY**

JOINT: This WPS shall be used in conjunction with the General Welding Standards (GWS) and Welding Fabrication Procedure (WFP) sections and criteria for joint details, repairs, NDE, inspection, etc.

Weld Joint Type: Butt

Class: Full & Partial Penetration & Fillets

See GWS 1-06 and WFP's for joint details.

Preparation: Faced Square Butt

Root Opening: <0.005

Backing: Gas

Backgrind Root: N/A

Backing Mat.: Gas

Bkgrd Method: N/A

GTAW Flux:

Backing Retainer: No

FILLER METALS:

A No: N/A

SFA Class: N/A

Class: N/A

F No: N/A

Size:

Insert: No

Insert Type: N/A

Weld Metal Thickness Ranges:

Flux: Type: N/A

Size:

AWS Root Pass:

Filler Material Note: Autogenous

AWS Balance:

ASME Root Pass:

ASME Balance: .077 thru .308

BASE MATERIAL:

Spec.: A-312 SS- Pipe

P No: 8

Gr No.: 1

to P No.: 8

Gr No.: 1

Qualified Pipe Dia. Range: >=

Grade: 316

to Spec.: A-312 SS- Pipe

Grade: 316

Qualified Thickness Range:

AWS:

ASME: 0.75

AWS:

ASME: 0.077 thru 0.308

QUALIFIED POSITIONS:

AWS:

ASME: All

Vert. Prog.: N/A

Preheat Min. Temp.: 70

GAS: Shielding: Ar/He or

Interpass Max. Temp.: N/A °F

Gas Composition: 25 / 75 / % / / %

Preheat Maintenance: 100 °F

Gas Flow Rate cfh: 20 to 40

PWHT: Time @ °F Temp.:

Backing Gas/Comp: Argon 100 %

Temperature Range:

Backing Gas Flow cfh: 0.5 to 1

Trailing Gas/Comp: N/A

WELDING CHARACTERISTICS:

Current: DCEP

Tungsten Type: EWCe-2

Transfer Mode:

Ranges: Amps: 40

Tungsten Dia.: .062 to 1/8

Pulsing Cycle:

Volts: 9

Background Current:

Fuel Gas: N/A

Flame: N/A

Braze Temp °F: N/A

WELDING TECHNIQUE: For fabrication specific requirements such as fitup, cleaning, grinding, PWHT and inspection criteria, refer to Volume 2, Welding Fabrication Procedures.

Technique: Automatic

Cleaning Method: Grind/wire brush/file

Single or Multi Pass: S or M

Stringer or Weave Bead (S/W): S

Oscillation: N/A

GMAW Gun Angle:

Forehand or Backhand for GMAW: N/A

No Pass > 1/2": Yes

GMAW/FCAW Tube to Work Distance (in): N/A

Maximum K/J Heat Input:

Travel Speed:

Gas Cup Size: N/A

PROCEDURE QUALIFIED FOR:

Charpy "V" Notch: No

Nil-Ductile Transition Temperature: No

Dynamic Tear: No

Comments: No comments.

Weld Layer	Manual Process	Filler Metals	Size	Amp Range	Volt Range	Travel/ipm	Nozzle Angle	Other
1	GTAW	N/A		40 to 150	9 to 14	1.25 to 2.0		
2								
3								
4								

REM. * Weld layers are representative only - actual number pf passes and layer sequence may vary.

ML-1/2 projects or jobs must determine if the supporting documentation for this WPS complies with quality requirements of the project/job.

Use of LANL Welding Procedures and Welder Qualifications for non-LANL work shall be at the sole risk and responsibility of the Subcontractor, and the Subcontractor shall indemnify and save LANL and the Government harmless from any and all claims, demands, actions or causes of action, and for any expense or loss by the reason of Subcontractor's and their employees posession and use of LANL procedures and qualifications.

APPROVAL: Signatures on file at ES-FE

DATE: