



WELDING PROCEDURE SPECIFICATION

WPS: 3503-xxxx-1

REV. NO.: 0

DATE: 10/7/2004

APPLICABILITY

WELDING PROCESS: FCAW and FCAW

CODE: ASME IX

OTHER:

SUPPORTING PQR: P-WS-243 P-WS-243-1

JOINT: This WPS shall be used in conjunction with the General Welding Standards (GWS) and Welding Fabrication Procedure (WFP) sections and criteria for joint details, repairs, NDE, inspection, etc.

Weld Joint Type: Groove/fillet**Class:** Full & Partial Penetration & Fillets**See GWS 1-06 and WFP's for joint details.****Preparation:** Mechanical/thermal**Root Opening:** 3/32 - 1/8**Backing:** Strap/ring**Backgrind Root:** Root if accessible**Backing Mat.:** CS when used**Bkgrd Method:** Grind/arc gouge**GTAW Flux:** N/A**Backing Retainer:** N/A**FILLER METALS:****Class:** E71-T-x and N/A**A No:** 1**SFA Class:** 5.20 and N/A**F No:** 6 and N/A**Size:** .045 N/A N/A N/A**Insert:** N/A**Insert Type:** N/A**Weld Metal Thickness Ranges:****Flux:** Type: N/A**Size:** N/A**AWS Root Pass:****AWS Balance:****ASME Root Pass:****ASME Balance:** 0.187 thru 2**Filler Material Note:** Flux core wire with Argon/CO2 gas shielding**BASE MATERIAL:**

Spec.: CS & AS- Pipe, plate, sheet & strip	P No: 1	Gr No.: All	to P No.: 1	Gr No.: All
Qualified Pipe Dia. Range: >=	Grade: All	to Spec.: CS & AS- Pipe, plate, sheet & strip		Grade: All
Qualified Thickness Range:	AWS:	ASME: 2.5		
	AWS:	ASME: 0.187 thru 2		

QUALIFIED POSITIONS:**AWS:** Plate-all**ASME:** Pipe-all**Vert. Prog.:** V-UP

Preheat Min. Temp.: 70	GAS: Shielding: Argon/CO2	or
Interpass Max. Temp.: 500 °F	Gas Composition: 75 / 25 / 0 %	0 / 0 / 0 %
Preheat Maintenance: 70 °F	Gas Flow Rate cfh: 25 to 40	0 to 0
PWHT: Time @ °F Temp.: N/A	Backing Gas/Comp: N/A	0 %
Temperature Range: N/A °F to N/A °F	Backing Gas Flow cfh: 0 to 0	
	Trailing Gas/Comp: N/A	0 %

WELDING CHARACTERISTICS:**Current:** DCEP and N/A**Tungsten Type:** N/A**Transfer Mode:** Spray**Ranges:** Amps: 130
Volts: 24**Tungsten Dia.:****Pulsing Cycle:** N/A to N/A**Fuel Gas:** N/A**Flame:** N/A**Background Current:** N/A**Braze Temp °F:** N/A to N/A

WELDING TECHNIQUE: For fabrication specific requirements such as fitup, cleaning, grinding, PWHT and inspection criteria, refer to Volume 2, Welding Fabrication Procedures.

Technique: Semi-auto man.**Cleaning Method:** Grind/wire brush/file**Single or Multi Pass:** M**Stringer or Weave Bead (S/W):** S/W**Oscillation:** N/A**GMAW Gun Angle:** 5 ° to 15 °**Forehand or Backhand for GMAW:** Forehand**No Pass > 1/2":****GMAW/FCAW Tube to Work Distance (in):** 3/8"-1/2"**Maximum K/J Heat Input:** N/A KJ/in**Travel Speed:** As reqd.**Gas Cup Size:** 1/2 - 5/8**PROCEDURE QUALIFIED FOR:****Charpy "V" Notch:** N/A**Nil-Ductile Transition Temperature:** N/A**Dynamic Tear:** N/A

Comments: *(1) Pipe dia. For AWS==24" OD (2)*IPT & pre-heat for =3/4" thick material =200 °F

Weld Layer	Manual Process	Filler Metals	Size	Amp Range	Volt Range	Travel/ipm	Nozzle Angle	Other
1	FCAW	E71-T-x	.045	130 to 150	24 to 26	4 to 6	5 to 15	
2	FCAW	N/A	N/A	140 to 180	26 to 28	5 to 10		
3	FCAW	N/A	N/A	0 to 0	0 to 0			
4	FCAW	N/A	N/A					

REM. * Weld layers are representative only - actual number pf passes and layer sequence may vary.

ML-1/2 projects or jobs must determine if the supporting documentation for this WPS complies with quality requirements of the project/job.

Use of LANL Welding Procedures and Welder Qualifications for non-LANL work shall be at the sole risk and responsibility of the Subcontractor, and the Subcontractor shall indemnify and save LANL and the Government harmless from any and all claims, demands, actions or causes of action, and for any expense or loss by the reason of Subcontractor's and their employees posession and use of LANL procedures and qualifications.

APPROVAL: Signatures on file at ES-FE

DATE: 10/7/2004